



IMPERSTOP "RR" con revestimiento retardador

Cinta de hinchamiento de bentonita para la impermeabilización económica de junta fría. La cinta de hinchamiento de bentonita IMPERSTOP R-R se caracteriza por un revestimiento nuevo, especial y patentado que retarda de 2-3 días un hinchamiento prematuro debido a la lluvia.

El revestimiento especial actúa según el valor de pH. La lluvia con valor de pH 7 (neutro) no disuelve el revestimiento durante 2-3 días. El revestimiento se disuelve químicamente durante la instalación con cemento fresco que tiene en cambio pH = 11 (básico, que puede variar ligeramente según la calidad del hormigón).

IMPERSTOP "RR" with retardant coating

Bentonite re-inflating tape for low-cost waterproofing connecting concrete castings.

The Imperstop "RR" inflating bentonite tape stands out for its new special patented coating that retards premature inflation due to rain by 2-3 days.

The special coating acts according to the pH value. Rain with a pH value of 7 (neutral) will not dissolve the coating for 2-3 days.

The special coating is chemically dissolved during installation with fresh cement, which instead has a pH value=11 (alkaline, it may vary slightly according to the quality of the concrete).

DATOS TÉCNICOS IMPERSTOP R-R 18 X 24

Material: Bentonita (Monimontonit), aglomerante, estuco, aditivos.

Revestimiento: Polímero especial, reacciona al valor de pH.

Certificados de pruebas: Hygiene Institut Gelsenkirchen (Certificado para agua potable) ACL Analytisch Chemisches Labor GmbH (diferentes certificados de pruebas).

Características del producto:

Revestimiento: Revestimiento especial 2µm. El valor de pH del cemento determina la solución química del revestimiento.

Medidas: 18 x 24 mm. **Peso:** 750 g/m. **Volumen de hinchado** >500% **Revestimiento especial patentado.**

TECHNICAL DATA FOR IMPERSTOP "RR" 18x24

Material: Bentonite (monimontonit), binder, filler, additives

Coating: special polymer, reacts to the pH value.

Test certificates: Hygiene Institut Gelsenkirchen (drinking water certificate) Acl Analytisch Chemisches Labor GmbH (various test certificates).

Product characteristics:

Coating: special 2µm coating. The cement's pH value determines the coating's chemical solution.

Size: 18x24 mm. **Weight:** 750 g/m. **Inflating volume** >500%. (special patented coating).

Waterstop bentonítico "RR" / "RR" bentonite Waterstop

Código Code	Denominación comercial Name	A mm	h mm	M Lm
490-010-200-018	Imperstop "RR" 24x18 con revestimiento retardador / with retardant coating	24	18	20